



HUBO RESOURCES CO. PTY. LTD

Specifications for CST 180		
Item	Guaranteed	Test Method
Density @ 20 Deg Celsius	0.86~0.88	ASTM D 4052
Kinematics Viscosity @ 40 Deg Celsius (CST)	MAX160	ASTM D 445
Flash Point (COC) Deg Celsius	MIN66	ASTM D 93
Pour Point Deg Celsius	< 6	ASTM D 97
Conradson Carbon wt %	< 0.5	ASTM D 4530
ASH wt %	< 0.01	ASTM D 482
Color ASTM	1.5~3.0	ASTM D 1500
Sulphur Content wt %	< 1.0	IP 242
Distillation (Dist 90%)	370~ 390	ASTM D 86
Mechanical Impurity	< 0.1	ASTM D
Water Content vol %	< 1.0	ASTM D 95
(E.D.Point)	420 ~ 440	